



GREEN SOLUTIONS GS900 Levelling Compound

FEATURES

- ✓ Installer Friendly
- ✓ Creating A Safer Work Environment
- ✓ Beneficial To Building Occupant
- ✓ Building Green Credits
- ✓ A Good Environmental Choice

RLA POLYMERS GREEN SOLUTIONS HIGH PERFORMANCE COMMERCIAL PRODUCTS are helping you to have a safer work place. During the installation period and for some further time, they will help improve the occupied work space air quality by reducing green house gas, solvent, organic and other volatile emissions.

GS900 is a self-smoothing cementitious underlayment specifically formulated for preparation of concrete sub floors prior to the laying of vinyl, carpet, tile and timber flooring.

The specially selected cements and polymers contained in GS900 produces an underlayment with exceptional adhesion to most prepared flooring materials. GS900 is suitable for sub floor heating.

PREPARATION

Sub floor must be free of oil grease, wax, curing compounds, dust, old adhesive and any other contaminations, which may inhibit bond. Diamond grinding, shot blasting or scarifying is the preferred method of preparation for large areas to remove any contamination.

Note: Concrete floors must be dry in accordance with A.S. 1884-1985 Appendix A 70% relative humidity maximum. Where temperatures less than 5°C or greater than 30°C are encountered, contact RLA technical staff for specific advice.

BENEFITS

- ✓ Green Star Compliant
- ✓ Solvent Free
- ✓ Very Low VOC Emission
- ✓ Anti-microbial Formulation
- ✓ Very Low Odour

PRIMING

Priming with GS450 or GS820 Moisture Sealing Compound is recommended to ensure good adhesion and reduce air release from the substrate, which causes pin boles of the underlayment.

Very absorbent concrete may require a second coat of primer.

NON POROUS FLOORS

For ceramic tiles, terrazzo, painted or epoxy surfaces and seated or burnished concrete floors please contact your RLA Polymers distributor.

MIXING

GS900 should be mixed using a drill and suitable paddle.

Use 1 bag (20 kg) GS900 with 5 litres of clean water. Slowly add 1/2 the bag of powder to the water while mixing thoroughly, and then add remainder of bag. Mix for 3 to 5 minutes to obtain a lump free mixture

Note: Do not over water as this will promote bleed and separation with a reduction in bond and tensile strength.

APPLICATION

Apply the mixed compound to the primed substrate using a screed bar or trowel to give the required thickness. Maximum thickness applied in any one application should be limited to 15mm. GS900 self smoothes in the first 10 minutes. Do not attempt to rework material after 10 minutes.



The application, use and processing of our products is the responsibility of the user. Any technical or other advice, information or data provided by us, whether verbally, in writing or by way of trials or tests, is given without guarantee or warranty. Refer to Material Safety Data Sheets for information on Storage & Handling, Health and Safety, and Transport.

RLA POLYMERS PTY LTD

ACN 004 709 915

215 Colchester Road, Kilsyth, Victoria 3137 Australia
P.O. Box 147, Kilsyth, Victoria 3137 Australia
Telephone: (03) 9728 1644 • Facsimile: (03) 9728 6009
E-mail: info@rlapolymers.com.au • Web: www.rlapolymers.com.au

vita A British Vita Group Company



67 Dalgety Drive (P.O. Box 97-575)
Manukau City, Auckland, New Zealand
Telephone: (9) 268 0301
Facsimile: (9) 268 0305

RLA 0448

PRODUCT
DATA

SOLUTIONS FOR INDUSTRY

CLEAN UP

Clean all equipment with water immediately after use.

PACKAGING

GS900: 20 Kg bags

STORAGE

GS900 is a cement-based product, which must be stored in a dry area off the ground and out of direct sun light.

TYPICAL PROPERTIES**Coverage**

Approximately 12 sq m to 14 sq m @ approx 1mm thick or 4 sq m to 4.5 sq m @ approx 3mm thick depending on texture of substrate.

Compressive Strength @ 20°C

1 day -12Mpa
7 days -24Mpa
28 days -30Mpa

Flow Work Time

10 minutes

Initial Set Times

1 hour @ 20°C

Ready for Adhesive

24 hrs @ 3mm @ 20°C

Thickness

Maximum 15mm, however at thicknesses greater than 15mm, a clean 4-6mm washed and dried aggregate may be added to promote economy, (contact your local RLA Polymers distributor for technical information).

GS900 can be feathered.

Adhesive

RLA flooring adhesives have been tested and recommended for use with GS900.

SAFETY & HANDLING

Material Safety Data Sheet available upon request.

Issued: November 2008